

1 The present invention relates to a hybrid
welding process and to a hybrid welding set combining a
laser beam and an electric arc, particularly a plasma
5 arc, using particular gas mixtures as assistance gases
for the laser beam and/or for the electric arc, and to
its application to the welding of pipes or of tailored
blanks.

10 Laser technology has been known and widely used
for years to weld various metallic materials, such as
workpieces made of alloy steels or non-alloy steels,
coated steels, stainless steels, aluminum and aluminum
alloys, or to weld pipes made of various metals.

15 In general, a laser welding set for welding
pipe comprises, apart from the means for feeding and
holding the pipe, a solid-state or gas laser oscillator
producing a coherent monochromatic high-energy beam, an
optical path provided with deviating mirrors or else an
optical fiber allowing the laser beam to be conveyed to
20 a welding head located opposite the pipe to be welded.

Conventionally, the welding head comprises a
lens or one or more focusing mirrors so as to focus the
laser beam onto one or more focal points in the
thickness of the material to be welded and in the joint
25 plane obtained by bringing together, edge to edge,
either the longitudinal edges of the metal sheet to be
welded so as to form a tube (i.e. to form an "O")
manufacturing a pipe, or the edges of the workpieces to
be joined together when welding several metal
30 workpieces to one another, for example tailored blanks,
so as to locally concentrate sufficient power density
to melt the material to be welded.

Usually, the welding head comprises a gas feed
device for feeding with welding gas, also called assist
35 gas, by means of a gas delivery nozzle placed coaxially
with the laser beam. This gas feed device may also be
external to the actual laser welding head.

09370044-053404

strip is firstly given a twist in a spiral movement so as to bring together or butt the two longitudinal edges of said strip in a joint plane having the form of a spiral or helix so as to form, here too, an unwelded pre-tube, this pre-tube then being subjected to helical welding so as to join the said two edges together in order to obtain a welded pipe.

Of course, in all cases the pre-tube and the welding head are driven so as to perform a movement of relative displacement one with respect to the other, that is to say either the pipe is stationary and the welding head moves, or vice versa.

The welding phase may be carried out in one or more passes and by using one or more welding processes according to the diameter and the thickness of the pre-tube to be welded.

These operations are carried out at high speed and it is important to use welding processes which allow the desired penetration to be obtained without slowing down the forming process, that is to say also a desired minimum speed making it possible to maintain maximum productivity or, in any case, the highest possible productivity.

Industrial pipe manufacturing lines very often use the multicathode welding process which employs, in general, several plasma or TIG electric arcs aligned in the welding joint plane.

Sometimes, laser welding is also used to weld the pipes. In particular, compared with the multicathode process, the use of a laser makes it possible to increase the speed but to the detriment of increased precision, which therefore requires much more precise alignment of the edges to be welded and precise control of the gap between the edges to be welded. This is very expensive from the standpoint of the tooling to be used.

By analogy, in the case of the welding of tailored blanks, like those intended for the automobile

09870044 053401

industry, it is necessary to join together two sheets or workpieces, generally made of steel, of galvanized steel, or of aluminum, of different thicknesses and/or different grades.

5 Depending on the welding methods and preparations used, the joint to be welded is often characterized by a difference in level between the upper planes of each of the workpieces to be welded, thus resulting in the creation of a "step", as shown in
10 figure 1. However, it is also possible to encounter the reverse situation, namely joints of the tailored-blank type in which the upper planes are aligned but the lower planes of which are not on the same level and where therefore the "step" is located on the reverse
15 side of the joint to be welded, as may be seen in figure 2. Furthermore, the case also exists in which the workpieces to be welded together have the same thickness but are of different grades from each other.

 Welds of this kind (figure 1 or figure 2) are
20 frequently found in the automobile industry in which the workpieces, once they have been welded, are pressed in order to give them their final shapes, for example, the various workpieces which are used in the manufacture of a car body, for example the doors, the
25 roof, the hood or the trunk. They may also be found in the structural elements of the passenger compartment.

 In order to improve the known processes for welding pipes or tailored blanks, it has been proposed to weld the edges together by using a hybrid welding
30 process which combines an electric arc with a laser beam, particularly a plasma arc and a laser beam.

 Apart from the abovementioned applications, a hybrid welding process is also well suited for welding many other types of joints and may, consequently, be
35 also used for, for example, the angle or corner welds shown schematically in figure 3 and the lap weld shown in figure 4.

09070014 0340
T0004

The use of a plasma/laser process, and more generally an arc/laser process, requires the use of a welding head which makes it possible to combine, in a small space, the laser beam and its focusing device, and a suitable welding electrode.

Several head configurations are described in the abovementioned documents and it may be stated, in summary, that the laser beam and the electric arc or plasma jet may be delivered by one and the same welding head, that is to say they leave via the same orifice, or else via two separate welding heads, one delivering the laser beam and the other the electric arc or plasma jet, the two coming together in the welding zone.

Arc/laser hybrid processes are reputed to be completely suitable for welding tailored blanks for the automobile industry, since they make it possible to obtain a weld bead which is well wetted and free of undercuts, as recalled in the documents EP-A-782 489 and "*Laser plus arc equal power*", *Industrial Laser Solutions*, February 1999, pages 28-30.

In general, when producing the welded joint, it is indispensable to use an assist gas for assisting the laser beam and for shielding the welding zone from external attack and a gas for the electric arc, particularly a plasma gas serving to create the plasma jet of the arc in the case of a plasma arc process.

However, it has been observed in practice that the results, that is to say the quality of the weld obtained, can vary considerably according to the gases used as laser-beam assist gas and as plasma gas.

In addition, because of possible incompatibilities between the gas and the workpieces to be welded by the hybrid process, it is not possible to use just any gas and in just any manner; in particular, it is usually recommended not to weld aluminum with a gas containing CO₂ or O₂ insofar as these compounds cause significant reduction in the mechanical properties of the weld obtained, that is to say they increase the risk of the weld failing.

Similarly, it is known that oxygen and carbon dioxide must not be brought into direct contact with the tungsten electrode used to generate the electric arc, in order not to damage it.

09070074 053101
TOP SECRET

Furthermore, to use a CO₂-based gas with a CO₂-type laser is not desirable since there is a risk of the CO₂ absorbing the energy of the laser beam.

Conversely, the presence of oxygen may be beneficial to the welding of certain materials such as steels. This is because, despite the presence of the laser welding plasma or of the metal vapors present in the interaction zone which will naturally be a site of fixing or confining the electric arc, it may prove necessary to further stabilize the electric arc, especially by injecting a little oxygen into the interaction zone so as to create on the surface of the puddle oxides onto which the electric arc will catch.

From these observations, it is one object of the invention therefore to provide an improved hybrid welding process allowing effective welding of workpieces made of various materials and using various gases or gas mixtures, used judiciously in order to avoid the abovementioned incompatibility problems and thus to be able to obtain quality welds.

The invention therefore relates to a hybrid process for welding one or more metal workpieces to be joined together by producing at least one welded joint between the edges to be welded of the said metal workpiece or workpieces, the said welded joint being obtained by using at least one laser beam and at least one electric arc, in which process, during welding of the joint, at least one part of the welding zone comprising at least one part of said welded joint is shielded during the operation with at least one shielding atmosphere formed by a gas mixture consisting of:

- argon and/or helium with a content greater than or equal to 70% by volume; and
- at least one additional compound chosen from H₂, O₂, CO₂ and N₂ with a content of 0 to 30% by volume.

5 - the content of at least one additional compound chosen from H_2 , O_2 , CO_2 and N_2 is non zero and less than or equal to 20% by volume, preferably non zero and less than or equal to 15% by volume;

- the shielding atmosphere is formed by a gas mixture consisting of argon with a content greater than or equal to 70% by volume and of 0.1 to 30% by volume of several additional compounds chosen from H_2 , O_2 , CO_2 and N_2 , preferably a mixture of argon, O_2 and CO_2 ;

30 - the shielding atmosphere is formed by a gas
mixture consisting of helium with a content greater
than or equal to 70% by volume and of 0.1 to 30% by
volume of several additional compounds chosen from H₂,
O₂, CO₂ and N₂, preferably a mixture of helium, O₂ and
35 CO₂ and furthermore possibly containing H₂;

- the shielding atmosphere is formed by a gas mixture consisting of at least 70% by volume of helium and argon and of 0.1 to 30% by volume of at least one

additional compound chosen from H_2 , O_2 , CO_2 and N_2 , preferably a gas mixture consisting of 0.1% to 69.9% by volume of helium, of 0.1% to 69.9% by volume of argon and of 0.1 to 30% by volume of at least one additional compound chosen from H_2 , O_2 , CO_2 and N_2 , the sum of the argon and helium contents being at least 70% of the total volume of the mixture;

- the workpiece or workpieces to be welded are made of a metal or a metal alloy chosen from coated or uncoated steels, particularly assembly steels, HLES steels, carbon steels, steels having a layer of zinc alloy on the surface, stainless steels, aluminum or aluminum alloys and high yield point steels;

- the shielding atmosphere is formed by a gas mixture consisting of at least 70% by volume of helium and/or argon and of 0.1 to 30% by volume of at least one additional compound chosen from O_2 and CO_2 and the workpiece or workpieces to be welded are made of steel, especially carbon steel;

- the shielding atmosphere is formed by a gas mixture consisting of at least 70% by volume of helium, of 0.1 to 30% by volume of hydrogen and of 0 to 29.9% by volume of at least one additional compound chosen from O_2 and CO_2 , and the workpiece or workpieces to be welded are made of stainless steel;

- the shielding atmosphere is formed by a gas mixture consisting of at least 90% by volume of helium or argon and of 0.1 to 10% by volume of at least one additional compound chosen from O_2 and CO_2 , and the workpiece or workpieces to be welded are made of aluminum, preferably of at least 96% by volume of helium or argon and of 0.1 to 4% by volume of at least one additional compound chosen from O_2 and CO_2 ;

- the shielding atmosphere is formed by a gas mixture consisting of at least 85% by volume of helium or argon and of 0.1 to 15% by volume of H_2 , and the workpiece or workpieces to be welded are made of

09870044 053101

stainless steel, preferably of at least 90% by volume of helium or argon and of 0.1 to 10% by volume of H₂;

5 - the shielding atmosphere is formed by a gas mixture consisting of at least 70% by volume of helium and/or argon and of 0.1 to 30% by volume of N₂, and the workpiece or workpieces to be welded are made of steel, preferably of at least 80% by volume of helium and/or argon and the balance being N₂;

10 - the shielding atmosphere is formed by a gas mixture consisting of at least 85% by volume of helium and/or argon and of 0.1 to 15% by volume of H₂ and CO₂, and the workpiece or workpieces to be welded are made of stainless steel;

15 - the laser beam is emitted by an Nd:YAG or CO₂ laser;

 - the electric arc is a plasma arc;

 - the electric arc is delivered by a plasma-arc torch and preferably the laser beam and said arc are delivered by a single welding head;

20 - the electrode is consumable or not consumable.

25 The invention also relates to the use of the above welding process for welding at least one tailored blank intended to constitute at least one part of a vehicle body element.

 The invention also relates to the use of the above welding process for joining together, by welding, metal workpieces having different thicknesses, particularly tailored blanks.

30 According to another aspect, the invention also relates to the use of the above welding process for joining together, by welding, metal workpieces having the same or different thicknesses and having different metallurgical compositions or metallurgical grades, particularly tailored blanks.

35 According to yet another aspect, the invention also relates to the use of the above welding process

09870014 053194
FOFES0 47002860

On account of the possible geometries of welding heads, of the hybrid processes according to the

invention and of the various means for feeding the gas or gas mixtures, the gas mixtures according to the

obtained in the interaction zone between the sheet or sheets to be welded and the laser and the arc,

independently of the manner in which they may have been created.

Given in the examples below are several types of gas mixtures that can be used to weld various mixtures according to the present invention.

Examples

Electric arc/laser hybrid welding with nonconsumable
electrode

5

Gas mixture	Contents (% by volume)	Material welded
Ar + He + H ₂	H ₂ : < 10 Ar + He : the balance	Stainless steels
Ar + H ₂	H ₂ : < 10 Ar : the balance	Stainless steels
He + H ₂	H ₂ : < 10 He : the balance	Stainless steels
Ar + He + CO ₂	CO ₂ : < 2 Ar + He : the balance	Stainless steels
Ar + CO ₂	CO ₂ : < 2 Ar : the balance	Aluminum
Ar + O ₂	O ₂ : < 2 Ar : the balance	Aluminum
He + CO ₂	CO ₂ : < 2 He : the balance	Aluminum
Ar + N ₂	N ₂ : < 20 Ar : the balance	Steels (any type)
He + N ₂	N ₂ : < 20 He : the balance	Steels (any type)
Ar + He + N ₂	N ₂ : < 20 He + Ar : the balance	Steels (any type)

1 2 3 4

Gas mixture	Contents (% by volume)	Material welded
Ar + He + CO ₂	CO ₂ : < 15 Ar + He : the balance	Carbon steels
Ar + He + O ₂	O ₂ : < 5 Ar + He : the balance	Carbon steels
Ar + CO ₂	CO ₂ : < 15 Ar : the balance	Carbon steels
Ar + O ₂	O ₂ : < 7 Ar : the balance	Carbon steels
He + CO ₂	CO ₂ : < 15 He : the balance	Carbon steels
He + O ₂	O ₂ : < 7 He : the balance	Carbon steels
Ar + CO ₂ + O ₂	O ₂ : < 5 CO ₂ : < 10 Ar : the balance	Carbon steels
He + CO ₂ + O ₂	O ₂ : < 5 CO ₂ : < 10 He : the balance	Carbon steels
Ar + He + CO ₂ + H ₂	H ₂ : < 2 CO ₂ : < 2 Ar : the balance	Stainless steels
Ar + CO ₂	CO ₂ : < 2 Ar : the balance	Aluminum Stainless steels
Ar + O ₂	O ₂ : < 2 Ar : the balance	Aluminum Stainless steels
He + CO ₂	CO ₂ : < 2 He : the balance	Aluminum Stainless steels
He + O ₂	O ₂ : < 2 He : the balance	Aluminum Stainless steels